



MENU

Results for COMPARISON O... >

Comparison of fracture resistance among restorative techniques for endod...

 Free Full Text from Publisher

View Full Text on ProQuest

Full Text Links ▾

Export ▾

Add To Marked List ▾

< 1 of 1 >

Comparison of fracture resistance among restorative techniques for endodontically treated mandibular premolars: an in vitro study

By

Are you this author?

Zulkifyly, DQ (Zulkifyly, Dinie Qurratuaini) ^[1]; Halil, MHM (Halil, Mohd Haikal Muhamad) ^[1]; Zamry, U (Zamry, Ubadah) ^[1]; Nor, SNHM (Nor, Siti Nabilah Huda Mohamad) ^[1]

[View Web of Science ResearcherID and ORCID](#) (provided by Clarivate)

Source

[SAUDI DENTAL JOURNAL](#)[← View Journal Impact](#)

Volume: 38 Issue: 7

DOI: 10.1007/s44445-026-00201-8

Article Number

91

Published JUN 22 2026**Early Access** JUN 2026**Indexed** 2026-06-26**Document Type** Article

Abstract Endodontically treated teeth often have compromised tooth structure, which increases their susceptibility to fracture. This in vitro study compared the fracture resistance of endodontically treated mandibular premolars restored using the sandwich technique, Nayyar core composite, and semi-direct composite onlay. Seventy-six extracted mandibular premolars were randomly allocated into four groups (n = 19): intact teeth (control), conventional sandwich technique, Nayyar core composite, and semi-direct composite onlay. All groups except the control teeth group underwent standardized root canal treatment and obturation, followed by composite restoration according to the group allocation. Specimens were loaded axially in a universal testing machine until fracture. Fracture resistance was recorded in kilonewtons (kN). Data were analyzed using one-way ANOVA and Dunnett T3 post-hoc tests ($p < 0.05$). Mean fracture resistance was highest in the intact control group (8.70 +/- 4.09 kN), followed by the sandwich technique (7.50 +/- 1.55 kN), Nayyar core composite (6.10 +/- 1.61 kN), and semi-direct composite onlay (4.94 +/- 3.16 kN). The overall difference among the groups was statistically significant ($p = 0.001$). Post-hoc analysis showed significant differences between the control and semi-direct onlay groups ($p = 0.019$) and between the sandwich technique and semi-direct onlay groups ($p = 0.022$). Within the limitations of this in vitro study, the sandwich technique demonstrated the highest fracture resistance when compared with Nayyar core composite restoration and semi-direct composite onlay in endodontically treated mandibular premolars with conservative access preparation and intact marginal ridges.

Keywords

Author Keywords: [Fracture resistance](#); [Endodontically treated teeth](#); [Sandwich technique](#); [Nayyar core composite](#); [Semi-direct composite onlay](#)

Keywords Plus: [CORONAL RESTORATIONS](#); [TEETH](#)

Author Information	Corresponding Address: Int Islamic Univ Malaysia, Dept Restorat Dent, Kulliyyah Dent, Bandar Indera Mahkota, Kuantan 25200, Pahang, Malaysia E-mail Addresses : drhaikal@iium.edu.my Addresses : ¹ Int Islamic Univ Malaysia, Dept Restorat Dent, Kulliyyah Dent, Bandar Indera Mahkota, Kuantan 25200, Pahang, Malaysia E-mail Addresses : dinie_q@iium.edu.my ; drhaikal@iium.edu.my ; ubadahzamry00@gmail.com ; hudamnor01@gmail.com
Data availability statement	All data supporting the findings of this study are available within the paper and its Supplementary Information.
Conflict of interest statement	The authors declare no competing interests.
Categories/ Classification	Research Areas: Dentistry, Oral Surgery & Medicine
Web of Science Categories	Dentistry, Oral Surgery & Medicine

+ See more data fields

Journal information

[SAUDI DENTAL JOURNAL](#)

← [View Journal Impact](#)

ISSN 1013-9052

eISSN 2524-1702

0.78

Journal
Citation
Indicator™
(2025)



Current Publisher SPRINGER NATURE, CAMPUS, 4 CRINAN ST,
LONDON N1 9XW, ENGLAND

Research Areas Dentistry, Oral Surgery & Medicine

Web of Science Categories Dentistry, Oral Surgery & Medicine

Citation Network

In Web of Science Core Collection

0 Citations

 [Create citation alert](#)

25

Cited References

[→ View Related Records](#)

How does this document's citation performance compare to peers?

[← Open comparison metrics panel](#)

Data is from InCites Benchmarking & Analytics

Use in Web of Science

0

Last 180 Days

0

Since 2013

[Learn more →](#)

This record is from:

Web of Science Core Collection

- Emerging Sources Citation Index (ESCI)

Suggest a correction

If you would like to improve the quality of the data in this record, please [Suggest a correction](#)

25 Cited References

[View as set
of results](#)

Showing 25 of 25

(from Web of Science Core Collection)

- 1 **Fracture resistance of
endodontically treated teeth
restored with indirect composite
inlay and onlay restorations - An *in
vitro* study**

20

[Citations](#)

42

[References](#)

Alshiddi, IF and Aljinbaz, A

Jan 2016 | [SAUDI DENTAL JOURNAL](#) ▼ 28(1),
pp.49-55[Free Full Text From Publisher](#) ...[Related records](#)